

Solo 977

Chemical Product	CAS #	BTT (minutes)	Permeation level	Standard	Degradatio level	Rating
2-Propanol (Isopropanol) 99%	67-63-0	48	2	EN 374-3:2003	3	+
Acetic acid 99%	64-19-7	2	0	EN 374-3:2003	NT	NA
Ammonium hydroxide solution 25%	1336-21-6	16	1	EN 374-3:2003	NT	NA
Ammonium hydroxide solution 29%	1336-21-6	15	1	EN 374-3:2003	4	+
Cyclohexane 99%	110-82-7	86	3	EN 374-3:2003	NT	NA
Ethanol 95%	64-17-5	5	0	EN 374-3:2003	NT	NA
Formaldehyde 37%	50-00-0	480	6	EN 16523-1:2015	3	++
Hydrochloric acid 10%	7647-01-0	NT	NT		4	NA
Hydrochloric acid 35%	7647-01-0	NT	NT		4	NA
Hydrochloric acid 37%	7647-01-0	54	2	EN 374-3:2003	4	+
Hydrogen peroxide 30%	7722-84-1	480	6	EN 16523-1:2015	NT	NA
Isooctane 99%	540-84-1	480	6	EN 374-3:2003	NT	NA
n-Butanol 99%	71-36-3	50	2	EN 374-3:2003	NT	NA
n-Heptane 99%	142-82-5	68	3	EN 374-3:2003	2	+
Sodium hydroxide 20%	1310-73-2	480	6	EN 16523-1:2015	NT	NA
Sodium hydroxide 40%	1310-73-2	480	6	EN 16523-1:2015	4	++
Sulfuric acid 10%	7664-93-9	480	6	EN 374-3:2003	4	++
Sulfuric acid 40%	7664-93-9	480	6	EN 374-3:2003	4	++
Sulfuric acid 50%	7664-93-9	480	6	EN 374-3:2003	4	++

*not normalized result

Overall Chemical Protection Rating

Protection rating is determined by taking into account the effects of both permeation and degradation in an attempt to provide users with an overall protection guideline when using our glove products against specific chemicals.

- Used for **high chemical exposure** or chemical immersion, limited to BTT based on a working day.
- Used for **repeated chemical contact**, limited to total chemical exposure i.e. : accumulative BTT based on a working day.
- **Splash protection only**, on chemical exposure the gloves should be discarded and new gloves worn as soon as possible.
- **Not recommended**, these gloves are deemed unsuitable for work with this chemical.

□ NT : Not tested

■ NA : Not applicable because not fully tested (only degradation OR permeation results)

The chemical test data and overall chemical protection rating should not be used as the absolute basis for glove selection. Actual in-use conditions may vary glove performance from the controlled conditions of laboratory tests. Factors other than chemical contact time