



aitex
textile research institute



ENAC
ENSAYOS
N°12 / LE025
N°12 / LE427

Tests marked with * are not included
within the scope of the ENAC accreditation

Honeywell Technology Solutions Lab Pvt Ltd
Plot No. 11, Survey No. 115, Road No. 2, IT PARK, Nanakramgud
IN-500019 Hyderabad

Att. Samit V. Chaudhari

**REPORT ISSUED BY THE RESEARCH ASSOCIATION OF THE TEXTILE
INDUSTRY, AITEX**

Nº 2020ID0091

The test was carried out at Polígono Industrial Fuente del Jarro. C/ Ciudad de Gibraltar, 5; 46988 – Paterna (Valencia); which property is shared at 50% between research institutes AITEX and ITE.



aitex
textile research institute



ITE
INSTITUTO TECNOLÓGICO DE
LA ENERGÍA

APPLICANT

HONEYWELL TECHNOLOGY SOLUTIONS LAB PVT LTD

Date of reception 03/11/2020

Date Test Starting: 03/11/2020
Ending: 23/11/2020

IDENTIFICATION AND DESCRIPTION OF SAMPLES

REFERENCES
Shirt INACC12RB Seri

TESTS CARRIED OUT

- MASS PER UNIT AREA.
- PRE-TREATMENT FOR DOMESTIC WASHING AND DRYING PROCEDURES FOR TEXTILE TESTING.
- STANDARD PRACTICE FOR DETERMINING RESPONSE CHARACTERISTICS AND DESIGN INTEGRITY OF ARC RATED FINISHED PRODUCTS IN AN ELECTRIC ARC EXPOSURE.

DESCRIPCIÓN DE MUESTRAS / *DESCRIPTION OF SAMPLES*

PHOTOGRAPHY



Reference⁽¹⁾
Shirt INACC12RB Seri

_____///

RESULTS/RESULTADOS

MASS PER UNIT AREA

Standard

ASTM D3776/3776M-09a (R2017) Option C

Conditioning date

03/11/2020

Test date

10/11/2020

Atmosphere for conditioning testing

Temperature (21±1) °C

Relative humidity

(65±2) %

Type of fabric

Woven fabric

State of the specimens

Original

Previous treatment

Null

Reference

Shirt INACC12RB Seri

Mass per unit area (oz/yd ²)	Mass per unit area (g/m ²)	Mass per unit area (oz/yd)	Mass per unit area (g/m)
9,87	334,55	2,16	66,91

///

RESULTS/RESULTADOS

PRE-TREATMENT FOR DOMESTIC WASHING AND DRYING PROCEDURES FOR TEXTILE TESTING

Standard

AATCC 135:2018

Standard deviation

Reference

Sample 1 Shirt INACC12RB Seri

Washing machine

13373I12

Washing cycles

3

Washing procedure

IV

Dryer machine

Whirlpool 13098I12

Drying procedure

Aiii

Washing powder

AATCC 1993 WOB

Start and finish date

04/11/2020 - 04/11/2020

///

RESULTS/RESULTADOS

MASS PER UNIT AREA

Standard

ASTM D3776/3776M-09a (R2017) Option C

Conditioning date

04/11/2020

Test date

10/11/2020

Atmosphere for conditioning testing

Temperature (21±1) °C

Relative humidity

(65±2) %

Type of fabric

Woven fabric

State of the specimens

Washed

Previous treatment

3 washing cycles, according to standard AATCC 135:2018, washed procedure 3/IV/Aiii

Reference

Shirt INACC12RB Seri

Mass per unit area (oz/yd ²)	Mass per unit area (g/m ²)	Mass per unit area (oz/yd)	Mass per unit area (g/m)
10,37	351,49	2,27	70,30

///

RESULTS/RESULTADOS

STANDARD PRACTICE FOR DETERMINING RESPONSE CHARACTERISTICS AND DESIGN INTEGRITY OF ARC RATED FINISHED PRODUCTS IN AN ELECTRIC ARC EXPOSURE

Test description

One garment was exposed to an arc incident energy level at least equal or above to Arc Rating of the fabric or fabric system used in garment construction. Following the arc exposure, the garment is examined. Areas of particular interest are seams, integrity of the closure systems, overlap of important areas, reflective trim or other accessories. The front area is examined for evidence of arc energy that may enter and expose the under-layers. A lightweight undergarment may be used to provide a heat sensitive indicator which is used to help in the evaluation of thermal energy through the closures or interface.

The following test data was recorded for each trial:

Arc exposure electrical conditions: arc trial number, RMS arc current, peak.

Temperature rise response from two monitor sensors for each Mannequin in each trial,
plot of average responses from two monitor sensors

Photographs before and after electric arc exposure

Video

>>>

STANDARD PRACTICE FOR DETERMINING RESPONSE CHARACTERISTICS AND DESIGN INTEGRITY OF ARC RATED FINISHED PRODUCTS IN AN ELECTRIC ARC EXPOSURE

Standard

ASTM F2621-2019

Reference

Shirt INACC12RB Seri

Test conditions	
Data test	20/11/2020
Stainless steel electrodes, gap of the electrodes	(300 ± 5) mm.
Distance between the electrodes and sample	(300 ± 5) mm.
Arc current	(8 ± 1) kA
Fuse wire	0.5 mm.
Number of samples tested	1
Starting and ending pre-treatment date	04/11/2020 - 04/11/2020

>>>

STANDARD PRACTICE FOR DETERMINING RESPONSE CHARACTERISTICS AND DESIGN INTEGRITY OF ARC RATED FINISHED PRODUCTS IN AN ELECTRIC ARC EXPOSURE


Sample tested	Mannequin A
Reference	Shirt INACC12RB Seri
Arc Rating	ATPV = 13 cal/cm ² 1208P49 - Arcwear
Pre-treatment	3 washing cycles at 49°C, according to standard AATCC TM135-2018, method 3IV and type Aiii drying
Garment layers and components According to the information supplied by the manufacturer	
Layer 1	Navy Blue woven fabric style 100C-320FR MaDEIRA-320, 100% Cotton, 320 g/m ² , manufacture XM textiles.
Closure Type(s)	Covered zipper closed by hook and loop.
Pockets	Two at chest with flap without closure system.
Reflective trim	One around chest and back. One at sleeves.
Others	Elastic at cuffs.
Indicator fabric	
Used in evaluation (yes/no)	Yes
Indicator fabric type	140 g/m ² 100% Cotton

>>>

STANDARD PRACTICE FOR DETERMINING RESPONSE CHARACTERISTICS AND DESIGN INTEGRITY OF ARC RATED FINISHED PRODUCTS IN AN ELECTRIC ARC EXPOSURE

Electrical current and response sensor plot:

Mannequin A Shirt INACC12RB Seri



Current Total RMS (kA)	7,9	Current Peak (kA)	17,3	Arc Voltage (V)	1404,0
Duration (cycles n°)	15,2	Duration (ms)	304,0	Arc Energy (kJ)	933,5

>>>

STANDARD PRACTICE FOR DETERMINING RESPONSE CHARACTERISTICS AND DESIGN INTEGRITY OF ARC RATED FINISHED PRODUCTS IN AN ELECTRIC ARC EXPOSURE

Results

Mannequin A Shirt INACC12RB Seri

Property	Mannequin A	Remark
Exposure level	15,26 cal/cm ²	
Burn	---	
After-flame	1 s.	
Break Open	No	
Ablation	No	
Melting or Dripping	No	
Charring	Yes	
Embrittlement	Yes	
Shrinkage	No	
Functioning of garment closures	Correct	
Indicator fabric evaluation	Without combustion	

>>>

**STANDARD PRACTICE FOR DETERMINING RESPONSE CHARACTERISTICS AND DESIGN INTEGRITY OF
ARC RATED FINISHED PRODUCTS IN AN ELECTRIC ARC EXPOSURE**

Pictures

Mannequin A Shirt INACC12RB Seri

Mannequin A
Original material



Tested material



>>>

Summary of results

GARMENT TESTED ACCORDING TO THE STANDARD ASTM F2621-2019

ATPV = 13 cal/cm²

To cover hazard/risk category 2 according to NFPA 70E

Arc Flash PPE category according to standard NFPA70E Edition 2018 Table 130.7 (C) (16) - Personal Protective Equipment (PPE)

PPE category	Minumum Arc Rating (cal/cm ²)
1	4
2	8
3	25
4	40

///

Lucia Martinez
Head of PPE and Ballistics department

LIABILITY CLAUSES

- 1.- AITEX is liable only for the results of the methods of analysis used, as expressed in the report and referring exclusively to the materials or samples indicated in the same which are in its possession, the professional and legal liability of the Centre being limited to these. Unless otherwise stated, the samples were freely chosen and sent by the applicant.
- 2.- AITEX shall not be liable in any case of misuse of the test materials nor for undue interpretation or use of this document
- 3.- The Offer and / or Order to which the applicant gives approval through signature and seal, constitutes the Legally Executable Agreement in which AITEX is responsible for safeguarding and guaranteeing the absolute confidentiality of the management of all the information obtained or created during the performance of the contracted activities.
- 4.- In the eventuality of discrepancies between reports, a check to settle the same will be carried out in the head offices of AITEX. Also, the applicants undertake to notify AITEX of any complaint received by them as a result of the report, exempting this Centre from all liability if such is not done, the periods of conservation of the samples being taken into account.
- 5.- AITEX is not responsible for the information provided by customers, which is reflected in the Report, and may affect the validity of the results.
- 6.- AITEX will provide at the request of the person concerned, the treatment of complaints procedure.
- 7.- AITEX is not responsible for an inadequate state of the sample received that could compromise the validity of the results, expressing such circumstance, in the test reports.
- 8.- AITEX may include in its reports, analyses, results, etc., any other evaluation which it considers necessary, even when it has not been specifically requested.
- 9.- When a Declaration of Conformity is requested, if not indicated otherwise, the decision rule will be applied according to ILAC-G8 & ISO 10576-1, in case of ambiguity, or indeterminacy
- 10.- The uncertainties of tests, which are made explicit in the Results Report, have been estimated for a $k = 2$ (95% probability of coverage). If not informed, they are available to the client in AITEX.
- 11.- The original materials and rests of samples, not subject to test, will be retained in AITEX during the twelve months following the issuance of the report, so that any check or claim which, in his case, wanted to make the applicant, should be exercised within the period indicated.
- 12.- This report may only be sent or delivered by hand to the applicant or to a person duly authorised by the same.
- 13.- The results of the tests and the statement of compliance with the specification in this report refer only to the test sample as it has been analyzed / tested and not the sample / item which has taken the test sample.
- 14.- The client must attend at all times, to the dates of the realization of the tests.
- 15.- According to Resolution EA (33) 31, the test reports must include the unique identification of the sample, and any brand or label of the manufacturer may be added. It is not allowed to re-issue test reports of untested sample names (references), they can only be re-issued for error correction or inclusion of omitted data that were already available at the time of the test. The laboratory can not assume responsibility for declaring that the product with the new trade name / trademark is strictly identical to the one originally tested; This responsibility belongs to the client.
- 16.- This report may not be partially reproduced without the written approval of the issuing laboratory.